


AMENDMENTS TO THE CLAIMS


This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:


1. (currently amended): An aromatic liquid-crystalline polyester film comprising an aromatic liquid-crystalline polyester with a weight average molecular weight of 5000 to 100000, which comprises by a structural unit of the following formula (I):



a structural unit of the following formula (II):




[[I]] wherein n represents 0 or 1[[I]], and a structural unit of the following formula (III):



wherein each structural unit combines through ester-bonding.

2. (original): The film according to Claim 1, wherein the aromatic liquid-crystalline polyester further comprises a structural unit of the following formula (IV):



(IV)

in addition to structural units of the formulae (I), (II) and (III).

3. (original): The film according to Claim 1, wherein the amount of (I) is from 40 to 70% by mol based on total structural units and (II)/(III) is from (95/100) to (100/95) in the molar ratio.

4. (original): The aromatic liquid-crystalline polyester film according to Claim 1 or 3, wherein the amount of (I) is from 55 to 60% by mol based on total structural units.

5. (original): The film according to Claim 1, wherein the structural unit (II) is a structural unit derived from hydroquinone and the structural unit (III) is a structural unit derived from 2,6-naphthalenedicarboxylic acid.

6. (original): The film according to Claim 2, wherein the amount of (I) is from 40 to 70% by mol based on total structural units, (III)/(IV) is from (95/5) to (5/95) in the molar ratio and (II)/[(III)+(IV)] is from (95/100) to (100/95) in the molar ratio.

7. (original): The film according to Claim 2, wherein the amount of (I) is from 55 to 60% by mol based on total structural units and (III)/(IV) is from (80/20) to (20/80) in the molar ratio.

8. (previously presented): The film according to Claim 2, wherein the structural unit (II) is a structural unit derived from hydroquinone, the structural unit (III) is a structural unit derived from 2,6-naphthalenedicarboxylic acid and the structural unit (IV) is a structural unit derived

from terephthalic acid, derived from isophthalic acid, or derived from a mixture of terephthalic acid and isophthalic acid.

9. (original): A laminated article obtained by laminating the film according to any one of Claim 1 or 2 and a metal layer.

10. (original): The laminated article according to Claim 9, wherein the metal layer is a metal layer of at least one metal selected from the group consisting of gold, silver, copper, nickel and aluminum.

11. (original): The laminated article according to Claim 10, wherein the metal layer is a copper layer.

12. (previously presented): A printed wiring board obtained by using the laminated body according to Claim 9.

13. (previously presented): A printed wiring board obtained by using the laminated body according to Claim 10.

14. (previously presented): A printed wiring board obtained by using the laminated body according to Claim 11.